

CORRECTED VERSION

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
8 September 2000 (08.09.2000)

PCT

(10) International Publication Number
WO 00/51566 A1

- (51) International Patent Classification⁷: A61K 9/14, 31/715, A61L 17/10, 27/20
- (21) International Application Number: PCT/US00/05610
- (22) International Filing Date: 3 March 2000 (03.03.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/122,814 4 March 1999 (04.03.1999) US
- (71) Applicant: UNITED STATES SURGICAL CORPORATION [—/US]; 150 Glover Avenue, Norwalk, CT 06856 (US).
- (72) Inventors: GRUSKIN, Elliott; A.; 23 Beach Tree Ridge, Killingworth, CT 06419 (US). CHRISTOFOROU, Christopher, T.; 4240 Katie Lane, Pleaston, CA 94566 (US).
- (74) Agent: FARBER, Mark; United States Surgical Corporation, 150 Glover Avenue, Norwalk, CT 06856 (US).
- (81) Designated States (*national*): AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN.
- (84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).
- Published:
— with international search report
- (48) Date of publication of this corrected version:
8 November 2001
- (15) Information about Corrections:
see PCT Gazette No. 45/2001 of 8 November 2001, Section II
Previous Correction:
see PCT Gazette No. 06/2001 of 8 February 2001, Section II
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: SCAR REDUCTION

(57) Abstract: A method of reducing scar formation at a wound site includes contacting the wound site with an effective scar reducing amount of a cross-linked polysaccharide having a positive charge and thereby reducing scar formation as the wound site heals. Such polysaccharide includes bioabsorbable cross-linked dextrans or alginates. The positive charge may be provided by diethylaminoethyl (DEAE) moieties. The cross-linked polysaccharide can be applied to the wound site as a powder or bead. The cross-linked polysaccharide may also be contained in a composition including a pharmaceutically acceptable vehicle. Biocompatible surgical devices are provided with an effective scar reducing amount of a cross-linked polysaccharide having a positive charge which reduce scar formation at healing wound sites. A method of reducing TGF- β activity is also provided.

WO 00/51566 A1

SCAR REDUCTION


BACKGROUND

1. Technical Field

This disclosure relates to reduction of scars associated with healing tissue. More particularly, wounds are treated with an oxidized cross-linked polysaccharide having a chemically induced charge.

2. Background of Related Art

Dextran is a polysaccharide which is produced from sucrose by bacteria belonging to the genera Leuconostoc, Streptococcus and Lactobacillus, all of which belong to the family Lactobacillaceae. The majority of known dextrans are formed by strains of Leuconostoc mesenteroides. A detailed discussion of dextran is provided in the Encyclopedia of Polymer Science and Engineering, Vol. 4, pp. 752 et seq. (1986) (John Wiley & Sons), hereby incorporated by reference. Dextran, in which 1 - 6 linkages predominate, may be represented as follows:



Certain dextran derivatives are well known. Dextran which is crosslinked with epichlorohydrin is described in U.S. Patent No. 3,042,667 and in British Patent No. 1,013,585 and is commercially available under the tradename SEPHADEX from Pharmacia Corp., Piscataway, New Jersey. Epichlorohydrin

(CH₂OCHCH₂Cl) reacts with the pendant hydroxyl groups on dextran to form ether bound bridges between dextran chains.

Various other derivatives of dextran are known. For example, see U.S. Pat. Nos. 4,963,666, (ester crosslinking), 4,591,638 (ester crosslinking), 2,988,455 (oxidized), 4,370,476 (ferric hydroxide complexes), 4,339,360 (activated oxidized) and 4,308,254 (oxidized support).

Dextran has been employed in the treatment of wounds. For example, an insoluble hydrophilic cross-linked dextran polymer in powder form has been used for the debridement of wounds, i.e., the removal of foreign bodies, pus, exudates and irrevocably damaged and devitalized tissue from tissue wounds. This dextran polymer, which is formed by crosslinking dextran with epichlorohydrin, is applied to heavily exudating wounds, allowed to gel and then washed out. The crosslinked dextran, commercially known as DEBRISAN®, absorbs the exudates, including the components that tend to impede tissue repair. Consequently, this composition promotes wound healing by retarding eschar formation and by keeping lesions soft and pliable.

Dextran derivatives have been used to promote hard tissue growth and repair and soft connective tissue growth and repair in mammals as described in U.S. Patent Nos. 4,988,358 and 5,092,883, respectively. In one aspect, SEPHADEX, a cross-linked dextran available from Pharmacia Corp., (Piscataway, NJ), linked with diethylaminoethyl (DEAE) functional groups as a basic anion exchanger is used for promoting soft tissue growth and repair by applying an effective quantity thereof to a site of tissue defect. The chemically induced surface charges promote soft connective tissue formation. In U.S. Patent No. 5,092,883, examples 4 and 5 indicate that positively charged DEAE-Sephadex beads are associated with stimulation effect on fibroblastic activity and that defects treated with the beads were filled with dense, highly cellular soft connective tissue. Wounds with positively charged beads are shown to be stronger than control wounds. There is, however, no recognition that scarring, which may typically be associated with healing wounds, can be reduced.

A scar is the mark left in the skin or an internal organ by new connective tissue that replaces tissue which has been injured by, e.g., burn, ulcer, abrasion, incision, etc. Scars may be viewed as unsightly defects which can result in psychological discomfort of people bearing such scars. As a result, the search for effective scar reducing measures has been ongoing. For example, as described in International Application No. PCT/GB92/00570, a composition for use in the treatment of wounds to inhibit scar tissue formation includes an activity-inhibiting amount of a growth factor neutralizing agent. It is therein indicated that TGF- β appears to be highly active in connection with organization of collagen leading to the formation of scar tissue. In accordance with PCT/GB92/00570, scar tissue formation is reduced by neutralizing TGF- β .

SUMMARY

A method of reducing scar formation at a wound site includes contacting the wound site with an effective scar reducing amount of a cross-linked polysaccharide having a positive charge and thereby reducing scar formation as the wound site heals. Such polysaccharide include bioabsorbable cross-linked dextrans or alginates. The positive charge may be provided by diethylaminoethyl (DEAE) moieties. The cross-linked polysaccharide can be applied to the wound site as a powder or bead. The cross-linked polysaccharide may also be contained in a composition including a pharmaceutically acceptable vehicle. Biocompatible surgical devices provided with an effective scar reducing amount of a cross-linked polysaccharide having a positive charge reduce scar formation at healing wound sites.

A method of reducing the activity of the TGF- β includes applying an effective TGF- β activity reducing amount of a cross-linked polysaccharide having a positive charge to a locus having TGF- β activity.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a graphic depiction of wound breaking strength in terms of Newtons over time comparing effect of degradable DEAE dextran with a methycellulose control;

Fig. 2 is a depiction of a control wound site at 28 days post-wounding;

5 Fig. 3 is a depiction of a wound site treated with degradable DEAE dextran at 28 days post-wounding;

Fig. 4 is a depiction of a control wound site at 7 days post-wounding;

Fig. 5 is a depiction of a wound site treated with degradable DEAE dextran at 7 days post-wounding;

10 Fig. 6 is a depiction of a control wound site at 10 days post-wounding;

Fig. 7 is a depiction of a wound site treated with degradable DEAE dextran at 10 days post-wounding;

Fig. 8 is a depiction of a control wound site at 14 days post-wounding;

15 Fig. 9 is a depiction of a wound site treated with degradable DEAE dextran at 14 days post-wounding;

Fig. 10 is a depiction of a control wound site at 21 days post-wounding;

Fig. 11 is a depiction of a wound site treated with degradable DEAE dextran at 21 days post-wounding; and

20 Fig. 12 is a graphical depiction of a percent change in the tensile strength of the DEAE Sephadex treated wounds compared to the control at various days in the study;

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS


25 The present method of reducing scar formation at a wound site includes contacting the wound site with an effective scar reducing amount of a cross-linked polysaccharide having a positive charge. The polysaccharide can be ionically or covalently cross-linked. Among the ionically cross-linked polysaccharides useful in preparing the present wound treatment compositions are alginic acid and pectic acid which complex with certain multivalent ions such as Ca^{++} to provide ionic cross-

linking. Among the covalently cross-linked polysaccharides, dextran and modified alginates are preferred for use in the present method. Cross-linked dextran is available under the tradename SEPHADEX from Pharmacia Corp., (Piscataway, New Jersey). Modified, covalently cross-linked alginates can be prepared, for example, as described in PCT WO 93/09176 which is incorporated herein by reference.


In a preferred embodiment, the cross-linked polysaccharide is biodegradable. Any known cross-linked biodegradable polysaccharide which can be made to carry a positive charge is suitable herein. For example, biodegradable cross-linked dextrans such as those described in U.S. Patent Nos. 4,963,666 and 4,591,638 are suitable. A biodegradable oxidized cross-linked polysaccharide having a chemically induced positive charge such as that described in U.S. Patent No. 5,502,042, the contents of which are incorporated herein by reference, is especially preferred.

Positive charges may be associated with cross-linked polysaccharides by any method known in the art. See, for example, U.S. Patent Nos. 4,988,358 and 5,092,883 to Eppley et al., the disclosures of which are incorporated herein by reference. In the case of oxidized cross-linked polysaccharide, positive chemical charge should be chemically induced on the polysaccharide, preferably prior to oxidation. For example, a positive charge can be provided on the polysaccharide by reaction with diethylamino ethyl chloride. Cross-linked dextran having DEAE groups thereon is commercially available under the name DEAE-SEPHADEX from Pharmacia Corp., Piscataway, New Jersey. The charged, cross-linked polysaccharide is oxidized to cleave a portion of the monosaccharide units to provide groups terminating in carboxyl groups.


Specifically, for example, in a dextran, the group:



oxidizes to either of the following two structures, depending on the oxidizing agent employed and the oxidizing conditions:



I



II

The linkages of structures I and II above are unstable and render the cross-linked polysaccharide biodegradable. The rate of biodegradation can be controlled by controlling the oxidation conditions to regulate the amount of monosaccharide units within the polysaccharides that are converted to structures I and/or II. Preferably, the oxidized, crosslinked polysaccharide will not completely lose its integrity until at least two days after application to a wound site.

Once prepared, the cross-linked positively charged polysaccharide can be applied directly to a wound site. When the wound is caused by traumatic and/or abrasive injury, the wound site is ordinarily debrided to remove extraneous material and reduce chance of infection. The positively charged polysaccharide is then applied to the wound site. In the case of surface wounds, the wound site containing the charged polysaccharide is then covered by bandage or other wound occluding devices known in

the art. If the wound runs deep into tissue, after application of the positively charged polysaccharide the wound may be closed by conventional surgical techniques such as suturing, stapling, etc. After sealing the wound site, the wound is allowed to heal while exhibiting markedly reduced scarring. Thus, for example, where DEAE-Sephadex has been oxidized, the beads can be sprinkled directly onto a wound site by sprinkling from a shaker or other container having one or more openings in its lid.

Application of positively charged polysaccharide to a wound in accordance with the present disclosure reduces the activity of TGF- β . Without wishing to be bound by any particular theory, it appears as though scar reduction is effected, at least in part, by the reduction of TGF- β activity. See International App. No. PCT/GB92/00570. Thus, by application of an effective amount of positively charged polysaccharide to a locus having TGF- β activity, the activity of TGF- β is reduced.

In particularly useful embodiments the cross-linked positively charged polysaccharide such as the oxidized cross-linked charged polysaccharide is mixed with a delivery vehicle to form a paste or fluid which can be applied to a wound. Any pharmaceutically acceptable biocompatible fluid can be used as the delivery vehicle. Where the delivery vehicle is based on water, saline or some other polar fluid, and the charged polysaccharide is biodegradable it may be necessary to take steps to avoid premature hydrolysis. For example, a scar reducing wound treatment can be provided as two separate components, namely the dry components (including the polysaccharide) in one container and the fluid component of the delivery vehicle in another container. The contents of the two containers are mixed shortly (preferably less than one hour) before application to the wound site. As another example, after mixing the polysaccharide and a polar delivery vehicle, the composition can be frozen to avoid premature hydrolysis. The scar reducing wound treatment could be thawed shortly before application to a wound site.

Alternatively, the polysaccharide can be mixed with a delivery vehicle based on a non-polar fluid. Suitable non-polar fluids include, mineral oil, non-ionic surfactants

liquid low molecular weight poly(ethylene oxide) and liquid low molecular weight poly(propylene oxide).

The viscosity of the scar reducing cross-linked polysaccharide will determine the method of its application. Thus, for example, low viscosity compositions can be
5 sprayed or poured onto a wound site. Compositions having a paste-like or gel-like viscosity can be applied to a wound site via spatula, syringe or from a tube.

It may be desirable to package the scar reducing cross-linked polysaccharide in a manner which prevents contact of the material with water. Known water impervious packages can be used. Additionally, the atmosphere within the package can be replaced
10 with a dry, inert gas. Alternatively, a desiccant can be placed within the package.

The scar reducing cross-linked polysaccharide can be sterilized using any technique which does not expose biodegradable material to excessive conditions which may cause premature degradation. Accordingly, ethylene oxide or gamma radiation are preferred sterilization methods.

The wound treatment composition including the positively charged
15 polysaccharide may optionally include additives such as fillers, colorants or viscosity modifiers. The wound treatment composition may also include a film-forming component if desired. Additionally, wound treatment composition may include one or more medico-surgically useful substances or therapeutic agent, e.g., those which
20 accelerate or beneficially modify the healing process when particles are applied to a surgical repair site. The therapeutic agent which will be deposited at the repair site. The therapeutic agent can be chosen for its antimicrobial properties, capability for promoting repair or reconstruction and/or new tissue growth. Antimicrobial agents such as broad spectrum antibiotic (gentamicin sulfate, erythromycin or VX
25 glycopeptides) which are slowly released into the tissue can be applied in this manner to aid in combating clinical and sub-clinical infections in a tissue repair site. To promote repair and/or tissue growth, one or several growth promoting factors can be incorporated, e.g., fibroblast growth factor bone morphogenetic protein, epidermal

growth factor, platelet derived growth factor, macrophage derived growth factor, alveolar derived growth factor, monocyte derived growth factor, magainin, and so forth. Some therapeutic indications are: glycerol with tissue or kidney plasminogen activator to cause thrombosis, superoxide dimutase to scavenge tissue damaging free radicals, tumor necrosis factor for cancer therapy or colony stimulating factor and interferon, interleukin-2 or other lymphokine to enhance the immune system. It is also contemplated that the medico-surgically useful substance may enhance blood coagulation. Thrombin is one such substance.

The scar reducing positively charged cross-linked polysaccharide may be applied to or incorporated in surgical devices for implantation into patients. For example, sutures can be coated or impregnated with scar reducing polysaccharides and then used to suture a wound. In the case of absorbable sutures, the presence of scar reducing polysaccharide minimizes scar formation at the wound site as the suture is absorbed. Bandages and other occlusive devices can be precoated with scar reducing polysaccharides for convenient application to surface wounds. Prosthetic devices known in the art such as artificial hips may be coated or impregnated with scar reducing polysaccharides. Cosmetic implants such as maxillofacial implants (see, for example, U.S. Pat. Nos. 5,554,194 or 5,496,371) can be provided with a coating of or be impregnated with scar reducing polysaccharides to reduce scarring of surrounding tissue after implantation.

The following non-limiting examples illustrative of the present disclosure.

EXAMPLE

Degradable DEAE Sephadex beads were suspended in a polyethylene glycol gel at a concentration of 10mg of beads per ml of PEG. The resulting composition was gamma sterilized and packaged in an aluminum tube. The composition was stored at room conditions until time of surgery.

275-350g male Sprague-Dawley rats were anesthetized and two parallel 6cm incisions were made, 1.5 cm either side of the spine. Wounds were closed with surgical staples (Multifire premium 35W, United States Surgical Corporation). Approximately 1 ml of composition was applied in one incision and saline was applied in the contralateral wound. At days 7, 10, 14, 21 and 28, the dorsal skin from ten rats were removed and 8mm strips perpendicular to the incision were excised. A total of three strips were taken from each wound. Matched-pair samples of experimental and control wounds from each rat were placed immediately after harvest into 10% buffered Formalin and embedded in paraffin by routine methods. The wounds were sectioned perpendicular to the incision and stained with hematoxylin and eosin.

There were 15 and 11 nodules in DEAE Sephadex treated samples at day 7 and day 10, respectively. The nodules were small localized bumps where excess material had accumulated. Such accumulation appeared to be the result of stapling on a loose skinned animal. These nodules subsided by day 14. At day 14, the treatment group was similar to the control group with no presence of nodules and this observation continued through day 28.

In wounds with degradable DEAE Sephadex beads at day 7, the beads were found at the base of the wound. The beads were intact spheres staining deep red in color. Histologically there was a mild inflammatory response at day 7 composed primarily of macrophage.

At days 10 and 14 the inflammation began to subside and the beads showed signs of mass loss, evidenced by the lack of deep red staining within the bead.

By days 21 and 28 the inflammation had subsided and the wounds were very well healed. The beads were further degraded as shown by the lighter straining and the presence of few beads. Figures 2-11 show representative examples of the histological findings.

As can be seen from Figs. 2 and 3, clear reduction in scarring resulted from treatment in accordance with the present disclosure. Figure 2 shows the control and

Fig. 3 the treated incisions 28 days post wounding. The control side shows a normal scar along the incision line. In the treated wound the incision line is not detectable.

In addition, the maximum load tolerated by wound strips prior to breaking was measured with a Tensometer (Monsanto, St. Louis, MO). Measurements were not performed on wounds showing evidence of infection, excessive hemorrhage, or poor coaptation. Samples for histology were taken from the cephalic and caudate ends of each wound.

The breaking strength for each wound was paired with its contralateral control and students paired t-tests were performed.

Tables 1 through 5 show wound breaking strength data in Newtons, for each wound strip, at every harvested time point. The data are paired as cephalic, medial and caudate wounds, where agent C is the degradable DEAE Sephadex (test group) and is the saline (control group).

Paired student t-tests show a significant difference in wound breaking strength between treated and control wounds at days 7, 10 and 14. The magnitude of the effect is 14.62%, 23.25% and 31.27% increases in wound breaking strength for the degradable DEAE Sephadex treated wounds at days 7, 10 and 14 respectively. At days 21 and 28, there is no significant difference between treatment and control. These results are shown graphically in figure 12.

In this study a single application of degradable DEAE Sephadex at the time of wound closure was shown to increase wound strength at days 7, 10 and 14. However, wound breaking strength is equivalent for bead treated and control wounds beyond day 17. Histology shows that the material is degradable and biocompatible. Degradable DEAE Sephadex applied to wounds at the time of wound closure is a safe procedure which is well tolerated by rats.

Table 1 shows wound breaking strength data in Newtons for each DEAE Sephadex and control wound strip at day 7 post wounding. Table 2 shows wound breaking strength data in Newtons for each DEAE Sephadex and control wound strip at

day 10 post wounding. Table 3 shows wound breaking strength data in Newtons for each DEAE Sephadex and control wound strip at day 14 post wounding. Table 4 shows wound breaking strength data in Newtons for each DEAE Sephadex and control wound strip at day 21 post wounding. Table 5 shows wound breaking strength data in Newtons for each DEAE Sephadex and control wound strip at day 28 post wounding.

It will be understood that various modifications may be made to the embodiments disclosed herein. For example, the compositions in accordance with this disclosure can be blended with other biocompatible, bioabsorbable or non-bioabsorbable materials. Any manner of surgical device can incorporate the charged polysaccharide. Therefore, the above description should not be construed as limiting, but merely as exemplifications of preferred embodiments. Those skilled in art will envision other modifications within the scope and spirit of the claims appended hereto.

TABLE 1

C/D (C-DEAE Sephadex; D-Control)) at Day 7						
	C#1	D #1	C#2	D #2	C#3	D #3
Rat #1	3.202	3.215	3.869	3.035	3.649	3.669
Rat #2	3.842	3.083	2.788	3.722	4.175	4.462
Rat #3	5.286	4.788	5.035	4.207	2.842	4.282
Rat #4	2.221	2.247	3.974	2.461	2.216	1.581
Rat #5	4.392	2.521	3.694	2.687	4.886	2.053
Rat #6	4.828	2.695	4.441	2.795	3.853	2.867
Rat #7	2.895	3.664	3.387	2.812	3.717	3.276
Rat #8	2.435	3.726	2.851	3.942	4.733	3.695
Rat #9	4.869	3.038	2.935	4.069	2.795	3.756
Rat #10	3.778	2.677	4.559	3.481	2.866	2.343
Mean	3.7748	3.1654	3.7533	3.3211	3.5732	3.1984
Std Dev	1.06912205	0.74084834	0.77317456	0.63906624	0.88303942	0.96178933
Paired Student t Test		0.03167586				
Percentage over control		14.62%				

TABLE 2

C/D (C-DEAE Sephadex; D-Control) at Day 10						
	C #1	D #1	C #2	D #2	C#3	D #3
Rat #1	6.597	5.723	6.016	5.056	6.791	5.836
Rat #2	5.536	4.729	4.548	4.181	3.795	2.802
Rat #3	6.003	5.596	5.942	3.195	5.796	5.105
Rat #4	5.807	4.239	5.834	4.927	6.397	4.289
Rat #5	5.298	4.017	6.195	2.957	6.221	3.218
Rat #6	5.886	3.938	4.387	3.328	3.289	2.429
Rat #7	3.186	3.386	2.847	4.931	3.729	5.338
Rat #8	5.732	4.882	6.882	5.582	6.285	4.899
Rat #9	4.197	2.185	3.578	3.229	4.539	3.513
Rat #10	6.175	5.498	6.286	5.659	5.283	4.376
Mean	5.4417	4.4193	5.2515	4.3045	5.2125	4.1805
Std Dev	1.0148688	1.10773363	1.32681593	1.05323251	1.28110224	1.14704444
Paired Student t Test		0.00106				
Percentage over control		23.25%				

TABLE 3

C/D (C-DEAE Sephadex; D-Control) at Day14						
	C #1	D #1	C #2	D #2	C#3	D #3
Rat #1	10.475	7.496	8.932	7.121	9.486	7.837
Rat #2	6.549	4.976	5.486	5.397	6.668	4.032
Rat #3	9.244	6.905	10.369	7.834	7.486	5.334
Rat #4	4.289	5.375	5.186	2.895	4.337	5.773
Rat #5	7.275	3.265	6.758	4.605	5.338	3.693
Rat #6	8.637	7.335	7.436	5.387	6.397	5.398
Rat #7	5.487	3.887	7.595	4.312	7.421	4.504
Rat #8	6.335	4.806	6.794	3.662	9.422	6.789
Rat #9	7.597	4.486	8.29	6.442	7.719	5.351
Rat #10	5.195	6.291	4.296	5.883	5.298	4.286
Mean	7.1083	5.4822	7.1142	5.3538	6.9572	5.2997
Std Dev	1.93356367	1.46609101	1.83048256	1.5382357	1.70563802	1.27987257
Paired Student t Test		0.00012666				
Percentage over control		31.27%				

TABLE 4

C/D (C-DEAE Sephadex; D-Control) at Day 21						
	C #1	D #1	C #2	D #2	C #3	D #3
Rat #1	18.458	16.773	15.118	17.741	14.147	18.713
Rat #2	20.008	18.324	20.042	21.225	10.188	12.128
Rat #3	17.093	13.055	12.939	13.639	17.394	17.834
Rat #4	19.748	14.238	14.354	12.055	10.273	11.226
Rat #5	12.335	19.375	10.365	17.639	9.194	15.327
Rat #6	18.364	20.446	19.767	17.826	18.337	14.236
Rat #7	11.765	12.687	15.829	16.202	14.374	16.832
Rat #8	14.376	17.284	11.846	18.391	13.827	17.028
Rat #9	17.449	11.769	15.695	20.162	17.238	18.827
Rat #10	19.438	17.253	12.756	13.668	15.793	12.558
Mean	16.9034	16.1204	14.8711	16.8548	14.0765	15.4709
Std Dev	3.03130761	2.99786495	3.16746665	2.95711894	3.26055037	2.80596276
Paired Student t Test		0.2816429				
Percentage over control		-5.35%				

TABLE 5

C/D (C-DEAE Sephadex; D-Control) at Day 28						
	C #1	D #1	C #2	D #2	C#3	D #3
Rat #1	29.045	27.395	24.193	26.193	27.394	25.834
Rat #2	25.495	22.194	28.394	22.394	26.295	24.164
Rat #3	34.291	31.201	32.119	30.183	31.038	28.371
Rat #4	28.464	29.934	27.925	32.849	25.355	30.284
Rat #5	24.047	25.284	22.283	23.956	28.374	26.331
Rat #6	29.338	23.183	27.334	28.574	22.219	27.384
Rat #7	30.234	31.394	28.586	26.445	33.921	25.236
Rat #8	32.747	29.384	33.194	34.295	32.185	30.182
Rat #9	25.394	26.338	24.283	32.471	26.483	29.745
Rat #10	32.918	25.184	30.184	29.221	27.112	25.383
Mean	29.1973	27.1491	27.8495	28.6581	28.0376	27.2914
Std Dev	3.47599597	3.2579654	3.50283045	3.92780633	3.47543328	2.24101069
Paired Student t Test		0.44053042				
Percentage over control		2.38%				

WHAT IS CLAIMED IS:

1. A method of reducing scar formation at a wound site comprising:
providing a scar reducing amount of a cross-linked polysaccharide
having a positive charge; and
5 contacting the wound site with an effective scar reducing amount of the
cross-linked polysaccharide having a positive charge and allowing the wound site to
heal thereby reducing scar formation at the healing site.

2. A method of reducing scar formation at a wound site according to claim 1
10 wherein the polysaccharide is a cross-linked dextran.

3. A method of reducing scar formation at a wound site according to claim 1
wherein the polysaccharide is contained in a composition including a pharmaceutically
acceptable vehicle.

4. A method of reducing scar formation at a wound site according to claim 3
15 wherein the composition is a powder.

5. A method of reducing scar formation at a wound site according to claim 3
20 wherein the composition is a gel.

6. A method of reducing scar formation at a wound site according to claim 3
wherein the composition is a non-polar fluid.

7. A method of reducing scar formation at a wound site according to claim 1
25 wherein the positive charge is provided by diethylaminoethyl moieties.

8. A method of reducing scar formation at a wound site according to claim 2 wherein the cross-linked dextran is bioabsorbable.

5 9. A method of reducing scar formation at a wound site according to claim 8 wherein the cross-linked dextran is oxidized.

10 10. A biocompatible surgical device comprising a structure adapted to contact living tissue, the structure having a scar reducing amount of a cross-linked polysaccharide having a positive charge.

11. A biocompatible surgical device according to claim 10 wherein the structure is a prosthetic implant.

15 12. A biocompatible surgical device according to claim 10 wherein the structure is a suture.

13. A biocompatible surgical device according to claim 12 wherein the suture is bioabsorbable.

20 14. A method of reducing the activity of TGF- β comprising applying an effective TGF- β activity reducing amount of a cross-linked polysaccharide having a positive charge to a locus having TGF- β activity.

25 15. A method of reducing the activity of TGF- β according to claim 14 wherein the polysaccharide is a cross-linked dextran.

16. A method of reducing scar formation at a wound site according to claim 14 wherein the polysaccharide is contained in a composition including a pharmaceutically acceptable vehicle.

5 17. A method of reducing scar formation at a wound site according to claim 14 wherein the positive charge is provided by diethylaminoethyl moieties.

18. A method of reducing scar formation at a wound site according to claim 15 wherein the cross-linked dextran is bioabsorbable.

10 19. A method of reducing scar formation at a wound site according to claim 18 wherein the cross-linked dextran is oxidized.


20. A method of increasing wound strength at a wound site for the first about 17 days of healing comprising:

15 providing a wound strengthening amount of a cross-linked polysaccharide having a positive charge; and

contacting the wound site with an effective wound strengthening amount of the cross-linked polysaccharide having a positive charge and allowing the wound site to heal thereby strengthening the wound at the healing site.

20

1/7

TIME COURSE OF INCISIONAL WOUND HEALING
IN RATS TREATED WITH DEGRADABLE
CHARGED POLYMER*Fig. 1*

2/7

Histology at day 28 for bead treated and control wounds



DAY 28 CONTROL

Control
Fig. 2




DAY 28 TREATED

Treated
Fig. 3

3/7

Histology at day 7 for bead treated and control wounds



Treated

Fig. 4



Control

Fig. 5

4/7

Histology at day 10 for bead treated and control wounds



Control

Fig. 6



Treated

Fig. 7

Histology at day 14 for bead treated and control wounds



Control

Fig. 8




Treated


Fig. 9

6/7

Histology at day 21 for bead treated and control wounds




Control
Fig. 10



Treated
Fig. 11

7/7

*Fig. 12*

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/05610

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) :A61K 9/14, 31/715; A61L 17/10, 27/20

US CL :424/488; 514/59; 606/230; 623/11

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 424/488; 514/59; 606/230; 623/11

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
EAST, MEDLINE, EMBASE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X --- Y	US 5,502,042 A (GRUSKIN et al) 26 March 1996, see entire document.	1-9, 14-20 ----- 10-13
Y	US 5,626,611 A (LIU et al) 06 May 1997, see entire document.	10-13
A.	US 5,532,221 A (HUANG et al) 02 July 1996, see entire document.	1-9, 14-20
A, P	US 5,885,609 A (AMIJI) 23 March 1999, see entire document.	1-20
A	US 5,690,961 A (NGUYEN) 25 November 1997, see entire document.	1-9, 14-20
Y	US 4,988,358 A (EPPLEY et al.) 29 January 1991, see entire document.	1-20

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	* & * document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

22 MAY 2000

Date of mailing of the international search report

12 JUL 2000

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

LEIGH C. MAIER

Telephone No. (703) 308-1235

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US00/05610

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This international report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

Please See Extra Sheet.

1. ☒ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest



The additional search fees were accompanied by the applicant's protest.



No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/05610

BOX II. OBSERVATIONS WHERE UNITY OF INVENTION WAS LACKING

This ISA found multiple inventions as follows:

This application contains the following inventions or groups of inventions which are not so linked as to form a single inventive concept under PCT Rule 13.1. In order for all inventions to be searched, the appropriate additional search fees must be paid.

Group I, claims 1-9 and 14-20, drawn to a method of reducing scar formation at a wound site using an amount of a cross-linked polysaccharide having a positive charge.

Group II, claims 10-13, drawn to a surgical device comprising a structure containing an amount of cross-linked polysaccharide having a positive charge.

The inventions listed as Groups I and II do not relate to a single inventive concept under PCT Rule 13.1 because, under PCT Rule 13.2, they lack the same or corresponding special technical features for the following reasons: The feature that links Groups I and II is the use of a cross-linked polysaccharide having a positive charge. Eppley et al (US 4,988,358) disclose the use of a cross-linked polysaccharide having a positive charge in a method for promoting hard tissue growth and repair in mammals. Therefore, the claims are not so linked by a special technical feature within the meaning of PCT Rule 13.2 so as to form a single general inventive concept.

CORRECTED VERSION

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
8 September 2000 (08.09.2000)

PCT

(10) International Publication Number
WO 00/51566 A1

- (51) International Patent Classification⁷: A61K 9/14, 31/715, A61L 17/10, 27/20
- (21) International Application Number: PCT/US00/05610
- (22) International Filing Date: 3 March 2000 (03.03.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 60/122,814 4 March 1999 (04.03.1999) US
- (71) Applicant: UNITED STATES SURGICAL CORPORATION [—/US]; 150 Glover Avenue, Norwalk, CT 06856 (US).
- (72) Inventors: GRUSKIN, Elliott, A.; 23 Beach Tree Ridge, Killingworth, CT 06419 (US). CHRISTOFOROU, Christopher, T.; 4240 Katie Lane, Pleaston, CA 94566 (US).
- (74) Agent: FARBER, Mark; United States Surgical Corporation, 150 Glover Avenue, Norwalk, CT 06856 (US).
- (81) Designated States (*national*): AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN.
- (84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).
- Published:
— With international search report.
- (48) Date of publication of this corrected version:
8 February 2001
- (15) Information about Correction:
see PCT Gazette No. 06/2001 of 8 February 2001, Section II
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: SCAR REDUCTION

(57) Abstract: A method of reducing scar formation at a wound site includes contacting the wound site with an effective scar reducing amount of a cross-linked polysaccharide having a positive charge and thereby reducing scar formation as the wound site heals. Such polysaccharide includes bioabsorbable cross-linked dextrans or alginates. The positive charge may be provided by diethylaminoethyl (DEAE) moieties. The cross-linked polysaccharide can be applied to the wound site as a powder or bead. The cross-linked polysaccharide may also be contained in a composition including a pharmaceutically acceptable vehicle. Biocompatible surgical devices are provided with an effective scar reducing amount of a cross-linked polysaccharide having a positive charge which reduce scar formation at healing wound sites. A method of reducing TGF- β activity is also provided.

WO 00/51566 A1

CORRECTED VERSION

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
8 September 2000 (08.09.2000)

PCT

(10) International Publication Number
WO 00/51566 A1

- (51) International Patent Classification⁷: A61K 9/14, 31/715, A61L 17/10, 27/20
- (21) International Application Number: PCT/US00/05610
- (22) International Filing Date: 3 March 2000 (03.03.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/122,814 4 March 1999 (04.03.1999) US
- (71) Applicant: UNITED STATES SURGICAL CORPORATION [—/US]; 150 Glover Avenue, Norwalk, CT 06856 (US).
- (72) Inventors: GRUSKIN, Elliott, A.; 23 Beach Tree Ridge, Killingworth, CT 06419 (US). CHRISTOFOROU, Christopher, T.; 4240 Katie Lane, Pleaston, CA 94566 (US).
- (74) Agent: FARBER, Mark; United States Surgical Corporation, 150 Glover Avenue, Norwalk, CT 06856 (US).
- (81) Designated States (*national*): AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN.
- (84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).
- Published:
— with international search report
- (48) Date of publication of this corrected version:
8 November 2001
- (15) Information about Corrections:
see PCT Gazette No. 45/2001 of 8 November 2001, Section II
Previous Correction:
see PCT Gazette No. 06/2001 of 8 February 2001, Section II
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: SCAR REDUCTION

(57) Abstract: A method of reducing scar formation at a wound site includes contacting the wound site with an effective scar reducing amount of a cross-linked polysaccharide having a positive charge and thereby reducing scar formation as the wound site heals. Such polysaccharide includes bioabsorbable cross-linked dextrans or alginates. The positive charge may be provided by diethylaminoethyl (DEAE) moieties. The cross-linked polysaccharide can be applied to the wound site as a powder or bead. The cross-linked polysaccharide may also be contained in a composition including a pharmaceutically acceptable vehicle. Biocompatible surgical devices are provided with an effective scar reducing amount of a cross-linked polysaccharide having a positive charge which reduce scar formation at healing wound sites. A method of reducing TGF- β activity is also provided.

WO 00/51566 A1

SCAR REDUCTION


BACKGROUND

1. Technical Field

This disclosure relates to reduction of scars associated with healing tissue. More particularly, wounds are treated with an oxidized cross-linked polysaccharide having a chemically induced charge.

2. Background of Related Art

Dextran is a polysaccharide which is produced from sucrose by bacteria belonging to the genera Leuconostoc, Streptococcus and Lactobacillus, all of which belong to the family Lactobacillaceae. The majority of known dextrans are formed by strains of Leuconostoc mesenteroides. A detailed discussion of dextran is provided in the Encyclopedia of Polymer Science and Engineering, Vol. 4, pp. 752 et seq. (1986) (John Wiley & Sons), hereby incorporated by reference. Dextran, in which 1 - 6 linkages predominate, may be represented as follows:



Certain dextran derivatives are well known. Dextran which is crosslinked with epichlorohydrin is described in U.S. Patent No. 3,042,667 and in British Patent No. 1,013,585 and is commercially available under the tradename SEPHADEX from Pharmacia Corp., Piscataway, New Jersey. Epichlorohydrin

(CH₂OCHCH₂Cl) reacts with the pendant hydroxyl groups on dextran to form ether bound bridges between dextran chains.

Various other derivatives of dextran are known. For example, see U.S. Pat. Nos. 4,963,666, (ester crosslinking), 4,591,638 (ester crosslinking), 2,988,455 (oxidized), 4,370,476 (ferric hydroxide complexes), 4,339,360 (activated oxidized) and 4,308,254 (oxidized support).

Dextran has been employed in the treatment of wounds. For example, an insoluble hydrophilic cross-linked dextran polymer in powder form has been used for the debridement of wounds, i.e., the removal of foreign bodies, pus, exudates and irrevocably damaged and devitalized tissue from tissue wounds. This dextran polymer, which is formed by crosslinking dextran with epichlorohydrin, is applied to heavily exudating wounds, allowed to gel and then washed out. The crosslinked dextran, commercially known as DEBRISAN®, absorbs the exudates, including the components that tend to impede tissue repair. Consequently, this composition promotes wound healing by retarding eschar formation and by keeping lesions soft and pliable.

Dextran derivatives have been used to promote hard tissue growth and repair and soft connective tissue growth and repair in mammals as described in U.S. Patent Nos. 4,988,358 and 5,092,883, respectively. In one aspect, SEPHADEX, a cross-linked dextran available from Pharmacia Corp., (Piscataway, NJ), linked with diethylaminoethyl (DEAE) functional groups as a basic anion exchanger is used for promoting soft tissue growth and repair by applying an effective quantity thereof to a site of tissue defect. The chemically induced surface charges promote soft connective tissue formation. In U.S. Patent No. 5,092,883, examples 4 and 5 indicate that positively charged DEAE-Sephadex beads are associated with stimulation effect on fibroblastic activity and that defects treated with the beads were filled with dense, highly cellular soft connective tissue. Wounds with positively charged beads are shown to be stronger than control wounds. There is, however, no recognition that scarring, which may typically be associated with healing wounds, can be reduced.

A scar is the mark left in the skin or an internal organ by new connective tissue that replaces tissue which has been injured by, e.g., burn, ulcer, abrasion, incision, etc. Scars may be viewed as unsightly defects which can result in psychological discomfort of people bearing such scars. As a result, the search for effective scar reducing measures has been ongoing. For example, as described in International Application No. PCT/GB92/00570, a composition for use in the treatment of wounds to inhibit scar tissue formation includes an activity-inhibiting amount of a growth factor neutralizing agent. It is therein indicated that TGF- β appears to be highly active in connection with organization of collagen leading to the formation of scar tissue. In accordance with PCT/GB92/00570, scar tissue formation is reduced by neutralizing TGF- β .

SUMMARY

A method of reducing scar formation at a wound site includes contacting the wound site with an effective scar reducing amount of a cross-linked polysaccharide having a positive charge and thereby reducing scar formation as the wound site heals. Such polysaccharide include bioabsorbable cross-linked dextrans or alginates. The positive charge may be provided by diethylaminoethyl (DEAE) moieties. The cross-linked polysaccharide can be applied to the wound site as a powder or bead. The cross-linked polysaccharide may also be contained in a composition including a pharmaceutically acceptable vehicle. Biocompatible surgical devices provided with an effective scar reducing amount of a cross-linked polysaccharide having a positive charge reduce scar formation at healing wound sites.

A method of reducing the activity of the TGF- β includes applying an effective TGF- β activity reducing amount of a cross-linked polysaccharide having a positive charge to a locus having TGF- β activity.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a graphic depiction of wound breaking strength in terms of Newtons over time comparing effect of degradable DEAE dextran with a methycellulose control;

Fig. 2 is a depiction of a control wound site at 28 days post-wounding;

5 Fig. 3 is a depiction of a wound site treated with degradable DEAE dextran at 28 days post-wounding;

Fig. 4 is a depiction of a control wound site at 7 days post-wounding;

Fig. 5 is a depiction of a wound site treated with degradable DEAE dextran at 7 days post-wounding;

10 Fig. 6 is a depiction of a control wound site at 10 days post-wounding;

Fig. 7 is a depiction of a wound site treated with degradable DEAE dextran at 10 days post-wounding;

Fig. 8 is a depiction of a control wound site at 14 days post-wounding;

15 Fig. 9 is a depiction of a wound site treated with degradable DEAE dextran at 14 days post-wounding;

Fig. 10 is a depiction of a control wound site at 21 days post-wounding;

Fig. 11 is a depiction of a wound site treated with degradable DEAE dextran at 21 days post-wounding; and

20 Fig. 12 is a graphical depiction of a percent change in the tensile strength of the DEAE Sephadex treated wounds compared to the control at various days in the study;

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS


25 The present method of reducing scar formation at a wound site includes contacting the wound site with an effective scar reducing amount of a cross-linked polysaccharide having a positive charge. The polysaccharide can be ionically or covalently cross-linked. Among the ionically cross-linked polysaccharides useful in preparing the present wound treatment compositions are alginic acid and pectic acid which complex with certain multivalent ions such as Ca^{++} to provide ionic cross-

linking. Among the covalently cross-linked polysaccharides, dextran and modified alginates are preferred for use in the present method. Cross-linked dextran is available under the tradename SEPHADEX from Pharmacia Corp., (Piscataway, New Jersey). Modified, covalently cross-linked alginates can be prepared, for example, as described
5 in PCT WO 93/09176 which is incorporated herein by reference.


In a preferred embodiment, the cross-linked polysaccharide is biodegradable. Any known cross-linked biodegradable polysaccharide which can be made to carry a positive charge is suitable herein. For example, biodegradable cross-linked dextrans such as those described in U.S. Patent Nos. 4,963,666 and 4,591,638 are suitable. A
10 biodegradable oxidized cross-linked polysaccharide having a chemically induced positive charge such as that described in U.S. Patent No. 5,502,042, the contents of which are incorporated herein by reference, is especially preferred.

Positive charges may be associated with cross-linked polysaccharides by any method known in the art. See, for example, U.S. Patent Nos. 4,988,358 and 5,092,883
15 to Eppley et al., the disclosures of which are incorporated herein by reference. In the case of oxidized cross-linked polysaccharide, positive chemical charge should be chemically induced on the polysaccharide, preferably prior to oxidation. For example, a positive charge can be provided on the polysaccharide by reaction with diethylamino ethyl chloride. Cross-linked dextran having DEAE groups thereon is commercially
20 available under the name DEAE-SEPHADEX from Pharmacia Corp., Piscataway, New Jersey. The charged, cross-linked polysaccharide is oxidized to cleave a portion of the monosaccharide units to provide groups terminating in carboxyl groups.


Specifically, for example, in a dextran, the group:



oxidizes to either of the following two structures, depending on the oxidizing agent employed and the oxidizing conditions:



I



II

The linkages of structures I and II above are unstable and render the cross-linked polysaccharide biodegradable. The rate of biodegradation can be controlled by controlling the oxidation conditions to regulate the amount of monosaccharide units within the polysaccharides that are converted to structures I and/or II. Preferably, the oxidized, crosslinked polysaccharide will not completely lose its integrity until at least two days after application to a wound site.

Once prepared, the cross-linked positively charged polysaccharide can be applied directly to a wound site. When the wound is caused by traumatic and/or abrasive injury, the wound site is ordinarily debrided to remove extraneous material and reduce chance of infection. The positively charged polysaccharide is then applied to the wound site. In the case of surface wounds, the wound site containing the charged polysaccharide is then covered by bandage or other wound occluding devices known in

the art. If the wound runs deep into tissue, after application of the positively charged polysaccharide the wound may be closed by conventional surgical techniques such as suturing, stapling, etc. After sealing the wound site, the wound is allowed to heal while exhibiting markedly reduced scarring. Thus, for example, where DEAE-Sephadex has been oxidized, the beads can be sprinkled directly onto a wound site by sprinkling from a shaker or other container having one or more openings in its lid.

Application of positively charged polysaccharide to a wound in accordance with the present disclosure reduces the activity of TGF- β . Without wishing to be bound by any particular theory, it appears as though scar reduction is effected, at least in part, by the reduction of TGF- β activity. See International App. No. PCT/GB92/00570. Thus, by application of an effective amount of positively charged polysaccharide to a locus having TGF- β activity, the activity of TGF- β is reduced.

In particularly useful embodiments the cross-linked positively charged polysaccharide such as the oxidized cross-linked charged polysaccharide is mixed with a delivery vehicle to form a paste or fluid which can be applied to a wound. Any pharmaceutically acceptable biocompatible fluid can be used as the delivery vehicle. Where the delivery vehicle is based on water, saline or some other polar fluid, and the charged polysaccharide is biodegradable it may be necessary to take steps to avoid premature hydrolysis. For example, a scar reducing wound treatment can be provided as two separate components, namely the dry components (including the polysaccharide) in one container and the fluid component of the delivery vehicle in another container. The contents of the two containers are mixed shortly (preferably less than one hour) before application to the wound site. As another example, after mixing the polysaccharide and a polar delivery vehicle, the composition can be frozen to avoid premature hydrolysis. The scar reducing wound treatment could be thawed shortly before application to a wound site.

Alternatively, the polysaccharide can be mixed with a delivery vehicle based on a non-polar fluid. Suitable non-polar fluids include, mineral oil, non-ionic surfactants

liquid low molecular weight poly(ethylene oxide) and liquid low molecular weight poly(propylene oxide).

The viscosity of the scar reducing cross-linked polysaccharide will determine the method of its application. Thus, for example, low viscosity compositions can be sprayed or poured onto a wound site. Compositions having a paste-like or gel-like viscosity can be applied to a wound site via spatula, syringe or from a tube.

It may be desirable to package the scar reducing cross-linked polysaccharide in a manner which prevents contact of the material with water. Known water impervious packages can be used. Additionally, the atmosphere within the package can be replaced with a dry, inert gas. Alternatively, a desiccant can be placed within the package.

The scar reducing cross-linked polysaccharide can be sterilized using any technique which does not expose biodegradable material to excessive conditions which may cause premature degradation. Accordingly, ethylene oxide or gamma radiation are preferred sterilization methods.

The wound treatment composition including the positively charged polysaccharide may optionally include additives such as fillers, colorants or viscosity modifiers. The wound treatment composition may also include a film-forming component if desired. Additionally, wound treatment composition may include one or more medico-surgically useful substances or therapeutic agent, e.g., those which accelerate or beneficially modify the healing process when particles are applied to a surgical repair site. The therapeutic agent which will be deposited at the repair site. The therapeutic agent can be chosen for its antimicrobial properties, capability for promoting repair or reconstruction and/or new tissue growth. Antimicrobial agents such as broad spectrum antibiotic (gentamicin sulfate, erythromycin or VX glycopeptides) which are slowly released into the tissue can be applied in this manner to aid in combating clinical and sub-clinical infections in a tissue repair site. To promote repair and/or tissue growth, one or several growth promoting factors can be incorporated, e.g., fibroblast growth factor bone morphogenetic protein, epidermal

growth factor, platelet derived growth factor, macrophage derived growth factor, alveolar derived growth factor, monocyte derived growth factor, magainin, and so forth. Some therapeutic indications are: glycerol with tissue or kidney plasminogen activator to cause thrombosis, superoxide dimutase to scavenge tissue damaging free radicals, tumor necrosis factor for cancer therapy or colony stimulating factor and interferon, interleukin-2 or other lymphokine to enhance the immune system. It is also contemplated that the medico-surgically useful substance may enhance blood coagulation. Thrombin is one such substance.

The scar reducing positively charged cross-linked polysaccharide may be applied to or incorporated in surgical devices for implantation into patients. For example, sutures can be coated or impregnated with scar reducing polysaccharides and then used to suture a wound. In the case of absorbable sutures, the presence of scar reducing polysaccharide minimizes scar formation at the wound site as the suture is absorbed. Bandages and other occlusive devices can be precoated with scar reducing polysaccharides for convenient application to surface wounds. Prosthetic devices known in the art such as artificial hips may be coated or impregnated with scar reducing polysaccharides. Cosmetic implants such as maxillofacial implants (see, for example, U.S. Pat. Nos. 5,554,194 or 5,496,371) can be provided with a coating of or be impregnated with scar reducing polysaccharides to reduce scarring of surrounding tissue after implantation.

The following non-limiting examples illustrative of the present disclosure.

EXAMPLE

Degradable DEAE Sephadex beads were suspended in a polyethylene glycol gel at a concentration of 10mg of beads per ml of PEG. The resulting composition was gamma sterilized and packaged in an aluminum tube. The composition was stored at room conditions until time of surgery.

275-350g male Sprague-Dawley rats were anesthetized and two parallel 6cm incisions were made, 1.5 cm either side of the spine. Wounds were closed with surgical staples (Multifire premium 35W, United States Surgical Corporation). Approximately 1 ml of composition was applied in one incision and saline was applied in the contralateral wound. At days 7, 10, 14, 21 and 28, the dorsal skin from ten rats were removed and 8mm strips perpendicular to the incision were excised. A total of three strips were taken from each wound. Matched-pair samples of experimental and control wounds from each rat were placed immediately after harvest into 10% buffered Formalin and embedded in paraffin by routine methods. The wounds were sectioned perpendicular to the incision and stained with hematoxylin and eosin.

There were 15 and 11 nodules in DEAE Sephadex treated samples at day 7 and day 10, respectively. The nodules were small localized bumps where excess material had accumulated. Such accumulation appeared to be the result of stapling on a loose skinned animal. These nodules subsided by day 14. At day 14, the treatment group was similar to the control group with no presence of nodules and this observation continued through day 28.

In wounds with degradable DEAE Sephadex beads at day 7, the beads were found at the base of the wound. The beads were intact spheres staining deep red in color. Histologically there was a mild inflammatory response at day 7 composed primarily of macrophage.

At days 10 and 14 the inflammation began to subside and the beads showed signs of mass loss, evidenced by the lack of deep red staining within the bead.

By days 21 and 28 the inflammation had subsided and the wounds were very well healed. The beads were further degraded as shown by the lighter staining and the presence of few beads. Figures 2-11 show representative examples of the histological findings.

As can be seen from Figs. 2 and 3, clear reduction in scarring resulted from treatment in accordance with the present disclosure. Figure 2 shows the control and

Fig. 3 the treated incisions 28 days post wounding. The control side shows a normal scar along the incision line. In the treated wound the incision line is not detectable.

In addition, the maximum load tolerated by wound strips prior to breaking was measured with a Tensometer (Monsanto, St. Louis, MO). Measurements were not performed on wounds showing evidence of infection, excessive hemorrhage, or poor coaptation. Samples for histology were taken from the cephalic and caudate ends of each wound.

The breaking strength for each wound was paired with its contralateral control and students paired t-tests were performed.

Tables 1 through 5 show wound breaking strength data in Newtons, for each wound strip, at every harvested time point. The data are paired as cephalic, medial and caudate wounds, where agent C is the degradable DEAE Sephadex (test group) and is the saline (control group).

Paired student t-tests show a significant difference in wound breaking strength between treated and control wounds at days 7, 10 and 14. The magnitude of the effect is 14.62%, 23.25% and 31.27% increases in wound breaking strength for the degradable DEAE Sephadex treated wounds at days 7, 10 and 14 respectively. At days 21 and 28, there is no significant difference between treatment and control. These results are shown graphically in figure 12.

In this study a single application of degradable DEAE Sephadex at the time of wound closure was shown to increase wound strength at days 7, 10 and 14. However, wound breaking strength is equivalent for bead treated and control wounds beyond day 17. Histology shows that the material is degradable and biocompatible. Degradable DEAE Sephadex applied to wounds at the time of wound closure is a safe procedure which is well tolerated by rats.

Table 1 shows wound breaking strength data in Newtons for each DEAE Sephadex and control wound strip at day 7 post wounding. Table 2 shows wound breaking strength data in Newtons for each DEAE Sephadex and control wound strip at

day 10 post wounding. Table 3 shows wound breaking strength data in Newtons for each DEAE Sephadex and control wound strip at day 14 post wounding. Table 4 shows wound breaking strength data in Newtons for each DEAE Sephadex and control wound strip at day 21 post wounding. Table 5 shows wound breaking strength data in Newtons for each DEAE Sephadex and control wound strip at day 28 post wounding.

It will be understood that various modifications may be made to the embodiments disclosed herein. For example, the compositions in accordance with this disclosure can be blended with other biocompatible, bioabsorbable or non-bioabsorbable materials. Any manner of surgical device can incorporate the charged polysaccharide. Therefore, the above description should not be construed as limiting, but merely as exemplifications of preferred embodiments. Those skilled in art will envision other modifications within the scope and spirit of the claims appended hereto.

TABLE 1

C/D (C-DEAE Sephadex; D-Control)) at Day 7						
	C #1	D #1	C #2	D #2	C #3	D #3
Rat #1	3.202	3.215	3.869	3.035	3.649	3.669
Rat #2	3.842	3.083	2.788	3.722	4.175	4.462
Rat #3	5.286	4.788	5.035	4.207	2.842	4.282
Rat #4	2.221	2.247	3.974	2.461	2.216	1.581
Rat #5	4.392	2.521	3.694	2.687	4.886	2.053
Rat #6	4.828	2.695	4.441	2.795	3.853	2.867
Rat #7	2.895	3.664	3.387	2.812	3.717	3.276
Rat #8	2.435	3.726	2.851	3.942	4.733	3.695
Rat #9	4.869	3.038	2.935	4.069	2.795	3.756
Rat #10	3.778	2.677	4.559	3.481	2.866	2.343
Mean	3.7748	3.1654	3.7533	3.3211	3.5732	3.1984
Std Dev	1.06912205	0.74084834	0.77317456	0.63906624	0.88303942	0.96178933
Paired Student t Test		0.03167586				
Percentage over control		14.62%				

TABLE 2

C/D (C-DEAE Sephadex; D-Control) at Day 10						
	C #1	D #1	C #2	D #2	C#3	D #3
Rat #1	6.597	5.723	6.016	5.056	6.791	5.836
Rat #2	5.536	4.729	4.548	4.181	3.795	2.802
Rat #3	6.003	5.596	5.942	3.195	5.796	5.105
Rat #4	5.807	4.239	5.834	4.927	6.397	4.289
Rat #5	5.298	4.017	6.195	2.957	6.221	3.218
Rat #6	5.886	3.938	4.387	3.328	3.289	2.429
Rat #7	3.186	3.386	2.847	4.931	3.729	5.338
Rat #8	5.732	4.882	6.882	5.582	6.285	4.899
Rat #9	4.197	2.185	3.578	3.229	4.539	3.513
Rat #10	6.175	5.498	6.286	5.659	5.283	4.376
Mean	5.4417	4.4193	5.2515	4.3045	5.2125	4.1805
Std Dev	1.0148688	1.10773363	1.32681593	1.05323251	1.28110224	1.14704444
Paired Student t Test		0.00106				
Percentage over control		23.25%				

TABLE 3

C/D (C-DEAE Sephadex; D-Control) at Day14						
	C #1	D #1	C #2	D #2	C#3	D #3
Rat #1	10.475	7.496	8.932	7.121	9.486	7.837
Rat #2	6.549	4.976	5.486	5.397	6.668	4.032
Rat #3	9.244	6.905	10.369	7.834	7.486	5.334
Rat #4	4.289	5.375	5.186	2.895	4.337	5.773
Rat #5	7.275	3.265	6.758	4.605	5.338	3.693
Rat #6	8.637	7.335	7.436	5.387	6.397	5.398
Rat #7	5.487	3.887	7.595	4.312	7.421	4.504
Rat #8	6.335	4.806	6.794	3.662	9.422	6.789
Rat #9	7.597	4.486	8.29	6.442	7.719	5.351
Rat #10	5.195	6.291	4.296	5.883	5.298	4.286
Mean	7.1083	5.4822	7.1142	5.3538	6.9572	5.2997
Std Dev	1.93356367	1.46609101	1.83048256	1.5382357	1.70563802	1.27987257
Paired Student t Test		0.00012666				
Percentage over control		31.27%				

TABLE 4

C/D (C-DEAE Sephadex; D-Control) at Day 21						
	C #1	D #1	C #2	D #2	C #3	D #3
Rat #1	18.458	16.773	15.118	17.741	14.147	18.713
Rat #2	20.008	18.324	20.042	21.225	10.188	12.128
Rat #3	17.093	13.055	12.939	13.639	17.394	17.834
Rat #4	19.748	14.238	14.354	12.055	10.273	11.226
Rat #5	12.335	19.375	10.365	17.639	9.194	15.327
Rat #6	18.364	20.446	19.767	17.826	18.337	14.236
Rat #7	11.765	12.687	15.829	16.202	14.374	16.832
Rat #8	14.376	17.284	11.846	18.391	13.827	17.028
Rat #9	17.449	11.769	15.695	20.162	17.238	18.827
Rat #10	19.438	17.253	12.756	13.668	15.793	12.558
Mean	16.9034	16.1204	14.8711	16.8548	14.0765	15.4709
Std Dev	3.03130761	2.99786495	3.16746665	2.95711894	3.26055037	2.80596276
Paired Student t Test		0.2816429				
Percentage over control		-5.35%				

TABLE 5

C/D (C-DEAE Sephadex; D-Control) at Day 28						
	C#1	D#1	C#2	D#2	C#3	D#3
Rat #1	29.045	27.395	24.193	26.193	27.394	25.834
Rat #2	25.495	22.194	28.394	22.394	26.295	24.164
Rat #3	34.291	31.201	32.119	30.183	31.038	28.371
Rat #4	28.464	29.934	27.925	32.849	25.355	30.284
Rat #5	24.047	25.284	22.283	23.956	28.374	26.331
Rat #6	29.338	23.183	27.334	28.574	22.219	27.384
Rat #7	30.234	31.394	28.586	26.445	33.921	25.236
Rat #8	32.747	29.384	33.194	34.295	32.185	30.182
Rat #9	25.394	26.338	24.283	32.471	26.483	29.745
Rat #10	32.918	25.184	30.184	29.221	27.112	25.383
Mean	29.1973	27.1491	27.8495	28.6581	28.0376	27.2914
Std Dev	3.47599597	3.2579654	3.50283045	3.92780633	3.47543328	2.24101069
Paired Student t Test		0.44053042				
Percentage over control		2.38%				

WHAT IS CLAIMED IS:

1. A method of reducing scar formation at a wound site comprising:
providing a scar reducing amount of a cross-linked polysaccharide
having a positive charge; and
5 contacting the wound site with an effective scar reducing amount of the
cross-linked polysaccharide having a positive charge and allowing the wound site to
heal thereby reducing scar formation at the healing site.

10 2. A method of reducing scar formation at a wound site according to claim 1
wherein the polysaccharide is a cross-linked dextran.

15 3. A method of reducing scar formation at a wound site according to claim 1
wherein the polysaccharide is contained in a composition including a pharmaceutically
acceptable vehicle.

4. A method of reducing scar formation at a wound site according to claim 3
wherein the composition is a powder.

20 5. A method of reducing scar formation at a wound site according to claim 3
wherein the composition is a gel.

6. A method of reducing scar formation at a wound site according to claim 3
wherein the composition is a non-polar fluid.

25 7. A method of reducing scar formation at a wound site according to claim 1
wherein the positive charge is provided by diethylaminoethyl moieties.

8. A method of reducing scar formation at a wound site according to claim 2 wherein the cross-linked dextran is bioabsorbable.

5 9. A method of reducing scar formation at a wound site according to claim 8 wherein the cross-linked dextran is oxidized.

10 10. A biocompatible surgical device comprising a structure adapted to contact living tissue, the structure having a scar reducing amount of a cross-linked polysaccharide having a positive charge.

11. A biocompatible surgical device according to claim 10 wherein the structure is a prosthetic implant.

15 12. A biocompatible surgical device according to claim 10 wherein the structure is a suture.

13. A biocompatible surgical device according to claim 12 wherein the suture is bioabsorbable.

20 14. A method of reducing the activity of TGF- β comprising applying an effective TGF- β activity reducing amount of a cross-linked polysaccharide having a positive charge to a locus having TGF- β activity.

25 15. A method of reducing the activity of TGF- β according to claim 14 wherein the polysaccharide is a cross-linked dextran.

16. A method of reducing scar formation at a wound site according to claim 14 wherein the polysaccharide is contained in a composition including a pharmaceutically acceptable vehicle.

5 17. A method of reducing scar formation at a wound site according to claim 14 wherein the positive charge is provided by diethylaminoethyl moieties.

18. A method of reducing scar formation at a wound site according to claim 15 wherein the cross-linked dextran is bioabsorbable.

10 19. A method of reducing scar formation at a wound site according to claim 18 wherein the cross-linked dextran is oxidized.

20. A method of increasing wound strength at a wound site for the first about 17 days of healing comprising:

15 providing a wound strengthening amount of a cross-linked polysaccharide having a positive charge; and

contacting the wound site with an effective wound strengthening amount of the cross-linked polysaccharide having a positive charge and allowing the wound site to heal thereby strengthening the wound at the healing site.

20

1/7

TIME COURSE OF INCISIONAL WOUND HEALING
IN RATS TREATED WITH DEGRADABLE
CHARGED POLYMER




Fig. 1

2/7

Histology at day 28 for bead treated and control wounds



Control
Fig. 2



Treated
Fig. 3

3/7

Histology at day 7 for bead treated and control wounds



Treated

Fig. 4



Control

Fig. 5

4/7

Histology at day 10 for bead treated and control wounds



Control

Fig. 6



Treated

Fig. 7

Histology at day 14 for bead treated and control wounds



Control

Fig. 8




Treated

Fig. 9


6/7

Histology at day 21 for bead treated and control wounds



DAY 21 CONTROL


Control
Fig. 10



DAY 21 TREATED

Treated
Fig. 11

7/7

*Fig. 12*

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US00/05610

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : A61K 9/14, 31/715; A61L 17/10, 27/20

US CL : 424/488; 514/59; 606/230; 623/11

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 424/488; 514/59; 606/230; 623/11

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EAST, MEDLINE, EMBASE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X --- Y	US 5,502,042 A (GRUSKIN et al) 26 March 1996, see entire document.	1-9, 14-20 ----- 10-13
Y	US 5,626,611 A (LIU et al) 06 May 1997, see entire document.	10-13
A	US 5,532,221 A (HUANG et al) 02 July 1996, see entire document.	1-9, 14-20
A, P	US 5,885,609 A (AMIJI) 23 March 1999, see entire document.	1-20
A	US 5,690,961 A (NGUYEN) 25 November 1997, see entire document.	1-9, 14-20
Y	US 4,988,358 A (EPPLEY et al.) 29 January 1991, see entire document.	1-20

☐ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

*	Special categories of cited documents:	"T"	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A"	document defining the general state of the art which is not considered to be of particular relevance		
"E"	earlier document published on or after the international filing date	"X"	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"L"	document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y"	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"O"	document referring to an oral disclosure, use, exhibition or other means		
"P"	document published prior to the international filing date but later than the priority date claimed	"&"	document member of the same patent family

Date of the actual completion of the international search

22 MAY 2000

Date of mailing of the international search report

12 JUL 2000

 Name and mailing address of the ISA/US
 Commissioner of Patents and Trademarks
 Box PCT
 Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

LEIGH C. MAIER

Telephone No. (703) 308-1235

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/05610

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This international report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:

3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

Please See Extra Sheet.

1. ☒ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:

4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☒ The additional search fees were accompanied by the applicant's protest.
☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/05610

BOX II. OBSERVATIONS WHERE UNITY OF INVENTION WAS LACKING

This ISA found multiple inventions as follows:

This application contains the following inventions or groups of inventions which are not so linked as to form a single inventive concept under PCT Rule 13.1. In order for all inventions to be searched, the appropriate additional search fees must be paid.

Group I, claims 1-9 and 14-20, drawn to a method of reducing scar formation at a wound site using an amount of a cross-linked polysaccharide having a positive charge.

Group II, claims 10-13, drawn to a surgical device comprising a structure containing an amount of cross-linked polysaccharide having a positive charge.

The inventions listed as Groups I and II do not relate to a single inventive concept under PCT Rule 13.1 because, under PCT Rule 13.2, they lack the same or corresponding special technical features for the following reasons: The feature that links Groups I and II is the use of a cross-linked polysaccharide having a positive charge. Eppley et al (US 4,988,358) disclose the use of a cross-linked polysaccharide having a positive charge in a method for promoting hard tissue growth and repair in mammals. Therefore, the claims are not so linked by a special technical feature within the meaning of PCT Rule 13.2 so as to form a single general inventive concept.

THIS PAGE BLANK (USPTO)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)